

AMENDMENTS TO THE CLAIMS

Please amend the claims as indicated below.

1. (Currently Amended) A multicomponent system comprising at least three components, comprising

(I) a component which is free from chlorinated polyolefins and is curable with polyisocyanates, comprising

(I.1) at least one binder containing isocyanate-reactive functional groups and

(I.2) at least one organic solvent

(II) a component free from binders (I.1), comprising

(II.1) at least one chlorinated polyolefin and

(II.2) at least one organic solvent,

(III) a component ~~consisting of or~~ comprising at least one polyisocyanate (III.1).

2. (Currently Amended) The multicomponent system as claimed in claim 1, wherein component (II) ~~contains~~comprises, based on its total amount

(II.1) from 5 to 40% by weight of at least one chlorinated polyolefin, calculated as solids.

3. (Currently Amended) The multicomponent system as claimed in claim 2, wherein component (II) ~~contains~~comprises, based on its total amount

(II.1) from 10 to 35% by weight of at least one chlorinated polyolefin.

4. (Currently Amended) The multicomponent system ~~as claimed in any one of claims 1 to 3~~1, wherein the chlorinated polyolefin (II.1) ~~contains~~comprises, based on its total amount, from 10 to 45% by weight of chlorine.

5. (Currently Amended) The multicomponent system ~~as claimed in any one of claims 1 to 4~~4, wherein the chlorinated polyolefin (II.1) ~~contains~~comprises, based on its total amount, from 15 to 20% by weight of chlorine.

6. (Currently Amended) The multicomponent system ~~as claimed in any one of claims 1 to 5~~, wherein component (I) comprises

(I.3) at least one additive.

7. (Currently Amended) The multicomponent system as claimed in claim 6, wherein the additive (I.3) is selected from the group consisting of physically curable binders other than the above-described binders (I.1); pigments; molecularly dispersely soluble dyes; light stabilizers, ~~such as UV absorbers and reversible free-radical scavengers (HALS)~~; antioxidants; wetting agents; emulsifiers; slip additives; antisetling agents; polymerization inhibitors; thermal crosslinking catalysts; thermolabile free-radical initiators; photoinitiators; ~~and photo-coinitiators~~; adhesion promoters; leveling agents; film-forming auxiliaries; rheological aids; ~~or rheological control additives~~ {thickeners; ~~and pseudoplastic sag control agents~~; SCA}; flame retardants; corrosion inhibitors; waxes, siccatives; biocides; ~~and/or dulling agents~~; and mixtures thereof.

8. (Currently Amended) The multicomponent system as ~~claimed in any one of~~ claims 1 ~~to 7~~, wherein organic solvents (I.2) and (II.2) ~~contain~~comprise isocyanate-reactive groups.
9. (Currently Amended) The multicomponent system as ~~claimed in any one of~~ claims 1 ~~to 8~~, wherein the isocyanate-reactive functional groups are selected from the group consisting of hydroxyl groups, thiol groups and primary and secondary amino groups.
10. (Currently Amended) The multicomponent system as ~~claimed in any one of~~ claims 1 ~~to 9~~, wherein component (III) comprises at least one inert organic solvent (III.2).
11. (Currently Amended) The multicomponent system as ~~claimed in any one of~~ claims 1 ~~to 10~~, further comprising at least one other component (IV).
12. (Currently Amended) A process for preparing ~~a~~the multicomponent system comprising as least three components as ~~claimed in any one of~~ claims 1 ~~to 11~~, which ~~comprising~~ing preparing components (I), (II) and (III) and, ~~where used, (IV)~~ separately from one another by mixing their respective constituents and homogenizing the mixtures.
13. (Currently Amended) A method of coating a substrate comprising applying ~~the~~ The use of a multicomponent system comprising at least three components as ~~claimed in any one of~~ claims 1 to a substrate~~11~~ or of a multicomponent system comprising at least three components and prepared by a process as claimed in claim ~~12~~ for preparing coating materials.
14. (Currently Amended) The method of ~~The use as claimed in claim 13,~~ wherein the coating materials are prepared by mixing components (I), (II) and (III) and, ~~where used, (IV)~~ and homogenizing the resulting mixtures.

15. (Currently Amended) The process of use ~~as claimed in claim 142~~, wherein components (I), (II) and (III) and, ~~where used (IV)~~ are mixed with one another in a proportion such that in the resulting coating materials the equivalent ratio of isocyanate-reactive functional groups to isocyanate groups is from 1:2 to 2:1.
16. (Currently Amended) The process use ~~as claimed in any one of claims 132 to 16~~, wherein the coating materials, based on their solids, contain from 0.5 to 15% by weight of at least one chlorinated polyolefin (II.1).
17. (Currently Amended) The method use ~~as claimed in any one of claims 13 to 16~~, wherein the multicomponent system is ~~coating materials are used for producing is an~~ adhesion-promoting and/or energy-absorbing coatings on ~~substrates~~.
18. (Currently Amended) The method use ~~as claimed in of claim 173~~, wherein the substrates comprises a ~~have~~ surface coatings comprising a ~~of~~ thermoplastics or thermoset materials ~~or consist thereof~~.
19. (Currently Amended) The method of claim 17 wherein the multicomponent comprises an use of component (II) as set forth in any one of claims 1 to 5 and of component (II) prepared by a process as claimed in claim 12 for producing ~~adhesion-promoting primer coatings having with a film thickness of up to 15 um, in particular 10 um, and the substrate comprises a~~ plastics.
20. (New) The method of claim 19 wherein the adhesion promoting primer coating has a film thickness of up to 10 um.